

Technical Properties of Stringybark

Species Name	Stringybark
Botanical Name	Blend a Stringybark species
Colour Range	Blonde
Janka (Hardness) Rating - Dry	8
Natural Durability Class	-
In-ground contact	3
Outside above ground contact	3
Density (kg/m³)	-
Unseasoned (Green)	1000
Seasoned (Dry)	750
Strength Group	-
Unseasoned (Green)	S5
Seasoned (Dry)	SD5
Joint Group	-
Unseasoned (Green)	J2
Seasoned (Dry)	JD2
Fire Indices	-
Spread-of-Flame Index	-
Smoke-Developed Index	-
Critical Radiant Flux	-
Smoke Development Rate	-
Group Number	-
Naturally bushfire-resisting Timber	UNKNOWN
Tangential Shrinkage %	6.1
Toughness (Nm)	
Naturally Unseasoned (Green)	
Seasoned (Dried)	-15
Naturally Termite Resistant to AS3660	RESISTANT
Naturally Lyctus Susceptible	SUSCEPTIBLE